



Heat Activated 100% Solids
Epoxy Resin System for
CIPP Applications

Overview

DESCRIPTION:

A one part epoxy system formulated to be used with a Warren approved fabric for cured in place pipelining. The catalyzed epoxy resin is stable at room temperature, there is no need for refrigeration

CHARACTERISTICS:

Formulated with special additives and modifiers to enhance the water resistance, chemical resistance, and bond strength to a variety of substrates as well as its own internal strength. When paired with an appropriate fabric system the liner is capable of negotiating multiple bends.

APPLICATION:

This product is sold and installed only by technicians specifically trained and licensed in our patented techniques.

Typical installation is steam or water inversion

RECOMENDED FABRICS

Warren Seamless S glass
Warren Seamless carbon fiber
Warren transitional felt system
Warren Kevlar liner

SPECIAL SAFETY AND HANDLING:

There are no special safety or handling procedures beyond those published on the reverse and the Material Safety Data Sheets.

Key Points

- **Adheres to a variety of substrates**
- **Excellent cure in high humidity**
- **100% solids**
- **0% VOC's**
- **Not DOT regulated**
- **Ready-to-use (DO NOT THIN)**
- **Single component No refrigeration necessary**
- **Capable of Negotiating multiple bends and turns**
- **For use with/in corrosive or harsh environments**
- **Shelf stable for up to 1 year**
- **Excellent water and chemical resistance**
- **Thinner CIPP thickness with superior strengths**

Typical Properties

| | |
|--|---------------|
| Viscosity | 1120 cps |
| Color | Yellow/ Brown |
| Gel time @ (100c) | 16 Minutes |
| Physical Properties (1/4" Casting) no fabric | |
| Tensile Strength (ASTM D638-86) | 6,223psi |
| Flexural Strength (ASTM D790-86) | 8,731 psi |
| Flexural Modulus @0.100" (ASTM D790-86) | 482,688 psi |
| Compressive Strength (ASTM D695-85) | 16,903 psi |
| Tensile Elongation @ Break | 4.7% |
| Shore D Hardness | 88 |
| Physical Properties with 1 ply Warren S Glass | |
| Sample thickness avg. | .07" |
| Tensile Strength (ASTM D638-86) | 19,416 psi |
| Flexural Strength (ASTM D790-86) | 43,191 psi |
| Flexural Modulus @0.100" (ASTM D790-86) | 1,172,939 psi |
| Tensile Elongation @ Break | 12.4% |
| Shore D Hardness | 88 |

Contact us at:
PO Box 1206, Carver, MA 02330

Tel. (508) 947-8539
www.warrenenviro.com

Fax (508) 947-3220

All values reported above are typical values, and are reported as a means of reference. Individual testing should be done to determine actual results, tested at specific conditions.

Mission Statement

Warren Environmental, Inc. will provide cost-effective coatings and methodologies that lead to permanent time-sensitive solutions meeting the structural rehabilitation needs of their customers. To this end, we pledge to use environmentally friendly materials, train and certify the people installing our products, and provide our customers a worry free experience.

Storage and Use

EPOXY COATINGS:

Are supplied in 50 gallon steel drums. The unmixed shelf life is one (1) year from date of purchase when stored indoors in their sealed original containers at a room temperature between 60°F and 80°F. When using this material, it is important to prevent cross contamination of the unused components. To assure proper performance, it is mandatory that the components be correctly identified and the mix ratio cited on the front of this bulletin be strictly followed.

CURED IN-PLACE PIPLINING SYSTEMS: this patented system may be provided in several different methodologies depending upon the application and field conditions. Warren Environmental, Inc. requires that these materials be installed by our licensed applicators only. These people are trained by us to address the issues unique to each situation. For more information please contact us.

General Surface Preparation Guidelines

Surfaces to be coated or adhered to should be cleaned of oil, grease, rust, scale, loose dirt and other contaminants that may hinder the adhesion of the epoxy coating to the substrate. In many instances cleaning the area to be coated of tuberculation and debris via scarifiers, sand blasting, or water will be sufficient. In rare instances such as oil covered metal, it may be necessary to treat the area with a solvent based cleaner. It is important to remove all traces of the solvent including fumes prior to applying the epoxy coating to ensure that no pinhole defects develop as the product cures. Concrete should be cured a minimum of 30 days prior to applying coating materials. Please contact us with specific questions regarding your application.

Warranty

Warren Environmental, Inc. warrants only that the product meets that quality and technical standards published in its current literature. Warren Environmental, Inc. cannot be held responsible for circumstances outside of its control including, but not limited to: product application, product handling, product storage, or any other conditions outside of our control. If within one (1) year from date of purchase, any product is proven by accepted industry standard test methods to be defective Warren Environmental, Inc. will, at its sole option, either replace or refund the purchase price of the product. These remedies shall constitute the sole and exclusive remedy for any claim under this warranty. This warranty is in lieu of any other warranties, expressed, implied, or statutory and is strictly limited to its terms.

If you witness any unethical or incorrect practices related to the application of any Warren Environmental product please contact us immediately at 508 947 8539

! ALWAYS READ SDS SHEETS BEFORE WORKING WITH ANY PRODUCT !

Contact us at:

PO Box 1206, Carver, MA 02330

Tel. (508) 947-8539
www.warrenenviro.com

Fax (508) 947-3220

All values reported above are typical values, and are reported as a means of reference. Individual testing should be done to determine actual results, tested at specific conditions.