



Warren Environmental, Inc.

S-301 Epoxy System Product Code 301-20 Duraflex

DESCRIPTION: A two part, 100% solids, room temperature curing, flexible hybrid epoxy system with enhanced flexibility for applications that require high performance within a wide temperature range.

CHARACTERISTICS: Formulated with special additives and modifiers to enhance the water resistance, chemical resistance, wear resistance, and bond strength to a variety of substrates as well as its own internal strength

APPLICATION: Designed to be applied with Warren Environmental dispensing equipment to a wide variety of substrates. The cured end product will yield a tough flexible tack free system that will perform within the temperature range of -10°C to $+110^{\circ}\text{C}$. This hybrid system features a convenient a Two (2) parts base to One (1) part activator mix ratio by volume. This product is sold and installed only by technicians specifically trained and approved in our patented techniques.

ADVANTAGES:

- Long Working Time Relative to Cure (28-Day Immersion) Time
- Flexibility Within a Wide Temperature Range.
- Excellent Cure at Low Temperature
- Excellent Cure at High Humidity
- % Zero Induction Time

CERTIFICATION:

None

SPECIAL SAFETY AND HANDLING: There are no special safety or handling procedures beyond those published on the reverse and the Material Safety Data Sheets.

Typical Properties

Liquid Properties (Systems)

Viscosity 90,000-120,000 cps
Thixotropic Index 5.0-6.0
Specific Gravity 1.143
Flash Point (Closed Cup) $>235^{\circ}\text{F}$
Color Varies
Gelttime (200g@ 77°F) 27 minutes
Thin Film Set (@ 77°F) 2 hours
Thin Film Set (@ 40°F) 8 hours

Physical Properties

(1/8" Casting)
Tensile Strength (ASTM D638-86) 1,030 psi
Flexural Strength (ASTM D790-86) N/A
Flexural Modulus @ 0.100" N/A
(ASTM D790-86)
Glass Transition Temperature 151°F
(ASTM D3418-82)
Tensile Elongation @ Break 41.7 %
Thin Film Set (@ 77°F) 2 hours
Shore D Hardness 55

Chemical Resistance

(28 Day Immersion)

Chemical Weight Gain (%)

Toluene 0.99
Ethanol 4.68
10% Acetic Acid 3.85
70% Sulfuric Acid 0.13
50% Sodium Hydroxide 0.09
Distilled Water 1.11
Methanol 9.55
Xylene 0.69
Butyl Cellosolve 1.18
Methyl Ethyl Ketone 11.19
10% Lactic Acid 3.24
Bleach 0.93
1,1,1 Trichloroethane 0.43
10% Nitric Acid 2.05
30% Nitric Acid 4.17

All values reported above are typical values and are reported as a means of reference.

MISSION STATEMENT

Warren Environmental, Inc. will provide cost-effective coatings and methodologies that lead to permanent time-sensitive solutions meeting the structural rehabilitation needs of their customers. To this end, we pledge to use environmentally friendly materials, train and certify the people installing our products, and provide our customers a worry free experience.

WARRANTY

Warren Environmental, Inc. warrants only that the product meets that quality and technical standards published in its current literature. Warren Environmental, Inc. cannot be held responsible for circumstances outside of its control including, but not limited to: product application, product handling, product storage, or any other conditions outside of our control. If within one (1) year from date of purchase, any product is proven by accepted industry standard test methods to be defective Warren Environmental, Inc. will, at its sole option, either replace or refund the purchase price of the product. These remedies shall constitute the sole and exclusive remedy for any claim under this warranty. This warranty is in lieu of any other warranties, expressed, implied, or statutory and is strictly limited to its terms.

STORAGE & USE

TWO-PART EPOXY COATINGS: are supplied in 50 gallon steel drums. The unmixed shelflife is one (1) year from date of purchase when stored indoors in their sealed original containers at a room temperature between 60°F and 80°F. When using this material, it is important to prevent cross contamination of the unused components. To assure proper performance, it is mandatory that the components be correctly identified and the mix ratio cited on the front of this bulletin be strictly followed.

CURED IN-PLACE PIPELINING SYSTEMS: this patented system may be provided in several different methodologies depending upon the application and field conditions. Warren Environmental, Inc. requires that these materials be installed by our licensed applicators only. These people are trained by us to address the issues unique to each situation. For more information please contact us.

SAFETY AND HANDLING

Material inadvertently applied to the skin should be washed immediately with lanolin based soap and warm water. Refer to the Material Safety Data Sheet for additional information.

GENERAL SURFACE PREPARATION GUIDELINES

Surfaces to be coated or adhered to should be cleaned of oil, grease, rust, scale, loose dirt and other contaminants that may hinder the adhesion of the epoxy coating to the substrate. In many instances cleaning the area to be coated of tuberculation and debris via scarifiers, sand blasting, or water will be sufficient. In rare instances such as oil covered metal, it may be necessary to treat the area with a solvent based cleaner. It is important to remove all traces of the solvent including fumes prior to applying the epoxy coating to ensure that no pinhole defects develop as the product cures. Concrete should be cured a minimum of 28 days prior to applying coating materials. Please contact us with specific questions regarding

Individual testing should be done to determine actual results, tested at specific conditions.

Contact us at:

PO Box 1206, Carver, MA 02330
www.warrenenviro.com

Tel. (508) 947-8539

Fax (508) 947-3220
E-mail: info@warrenenviro.com